

試驗報告



報告編號：KV-19-10327-1

頁數：1 OF 1

報告日期：108年12月09日

南亞塑膠工業股份有限公司

產品名稱：南亞 PVC 防水夾網膠皮

產品顏色：0Y1/089

送驗廠商：南亞塑膠工業股份有限公司

收件日期：108年11月29日

試驗日期：108年11月29日~108年12月09日

產品規範 CNS 10145(2016) 合成聚合物薄片防水膠布(複合薄片-補強複合型)

試驗方法 CNS 10145(2016) 合成聚合物薄片防水膠布

備註：1.以上資料由顧客提供(收件及試驗日期除外)

2.除非另有說明，此報告結果僅對測試之樣品負責
未經本公司事先書面同意，此報告不可部分複製

3.下述報告內容標示#處由顧客提供

試驗結果：

試驗項目			試驗結果	#要求值
搭接拉伸性能	搭接抗拉強度(N/cm)	無處理	515	≥ 240


註：1.實驗室測試環境：溫度(20±2)℃，相對濕度(65±5)%。

2.試片養護條件：溫度(20±2)℃，相對濕度(65±5)%，1小時以上。

3.本試驗報告取代 KV-19-10327，原試驗報告作廢，報告修改日期 108年12月27日，更正產品名稱。

----- oOo -----

本報告若有提供規範值，該規範值僅供參考，合格之判定以委託單位實際要求為準


 報告簽署人

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.

試驗報告



報告編號：KV-19-05910-1

頁數：1 OF 1

報告日期：108年12月09日

南亞塑膠工業股份有限公司

產品名稱：南亞 PVC 防水夾網膠皮

產品顏色：0Y1/089

送驗廠商：南亞塑膠工業股份有限公司

收件日期：108年07月11日

試驗日期：108年07月11日~108年12月09日

產品規範 CNS 10145(2016) 合成聚合物薄片防水膠布(複合薄片-補強複合型)

產品規範：CNS 10145(2016) 合成聚合物薄片防水膠布

備註：1.以上資料由顧客提供(收件及試驗日期除外)

2.除非另有說明，此報告結果僅對測試之樣品負責
未經本公司事先書面同意，此報告不可部分複製

3.下述報告內容標示#處由顧客提供

試驗結果：

試驗項目	試驗結果		#要求值	
	長度方向	寬度方向		
拉伸性能	抗拉強度(N/cm)	455	507	≥ 240
	伸長率(%)	29.1	21.5	≥ 15
撕裂性能	直角型撕裂強度(N)	105	122	≥ 50
搭接拉伸性能	搭接抗拉強度(N/cm)	無處理	530	≥ 240


註：1.實驗室測試環境：溫度(20±2)℃，相對濕度(65±5)%。

2.試片養護條件：溫度(20±2)℃，相對濕度(65±5)%，1小時以上。

3.本試驗報告取代 KV-19-05910，原試驗報告作廢，報告修改日期 108年12月27日，更正產品名稱與刪除供應廠商。

----- oOo -----

本報告若有提供規範值，該規範值僅供參考，合格之判定以委託單位實際要求為準



報告簽署人

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.



材料暨工程實驗室-高雄

試驗報告



報告編號：KV-19-05909-1

頁數：1 OF 1

報告日期：108年11月13日

南亞塑膠工業股份有限公司

- 產品名稱：南亞 PVC 防水夾網膠皮
- 產品顏色：0Y1/089
- 送驗廠商：南亞塑膠工業股份有限公司
- 收件日期：108年07月11日
- 試驗日期：108年07月11日~108年11月11日
- 備註：
 1. 以上資料由顧客提供(收件及試驗日期除外)
 2. 除非另有說明，此報告結果僅對測試之樣品負責
未經本公司事先書面同意，此報告不可部分複製
 3. 下述報告內容標示#處由顧客提供

試驗結果：

試驗項目		試驗方法	試驗結果
耐化學性 (23 °C, 24 h)	5 % 硫酸	ASTM D543-14	外觀無明顯變化
	5 % 氫氧化鈉		外觀無明顯變化
耐候試驗(1000 h)			
a. 外觀		ASTM G154-16 Cycle 1	無異狀
b. 灰色標		ASTM D2616-12	4~5

註：1. 耐候試驗條件：

燈管：UVA - 340

照射能量：0.89 (W/m²·nm) 在 340 nm

每一循環條件：(1) 8小時照光；黑板溫度：(60 ± 3) °C;

(2) 4小時冷凝；黑板溫度：(50 ± 3) °C;

2. 本試驗報告取代KV-19-05909，原試驗報告作廢，報告修改日期 108年12月27日。

修改樣品名稱。

----- oOo -----

報告簽署人

本報告若有提供規範值，該規範值僅供參考，合格之判定以委託單位實際要求為準

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.